

<b>Properties</b>	<b>KC-11</b>	<b>KC-2</b>
Apparant Density ( gm/ml)	0.42 - 0.47	0.40-0.45
Surface Area by Nitrogen Absorption M2/g	20-23	13-15
Specific Surface Diameter(um)	0.11	0.16
DOP Absorption (gm/100 gm)	65-80	60-75
Fineness % (through 45 micron min)	99.70	99.70
Crystalline Habit	Calcite	Semi-Calcite